

PATENT

UTILITY CERTIFICATE - CERTIFICATE OF ADDITION

OFFICIAL COPY

The Director-General of the Institut National de la Propriété Industrielle certifies that the attached document is a true copy of an application for industrial property titleright filed at the Institute.

Drawn up	in	Paris,	08 JAN. 2004
Diami up		,	

On behalf of the Director-General of the Institut National de la Propriété Industrielle The Patent Department Head

[signature]

Martine PLANCHE

[Stamp: PRIORITY DOCUMENT SUBMITTED OR TRANSMITTED IN COMPLIANCE WITH RULE 17.1.a) OR b)

REGISTERED OFFICE

IN STITUT 26 bis, rue de Saint Petersbourg

NATIONAL DE 75800 PARIS Cédex 08

Talephone. 33 (0)1 53 04 53 04

Fax 33 (0)1 53 04 45 23

www.inpi.fr



PATENT

UTILITY CERTIFICATE

Intellectual Property Code - Book VI

REQUEST FOR GRANT



26 bis, rue de Saint Pétersbourg 75800 Paris Cedex 08

Reserved for the INPI

Telephone: 33 (1) 53 04 53 04 Fax: 33 (1) 42 94 86 54

page 1/2

This form is to be filled in legibly in black ink DB 540 ⊗ W / 210502

SUBM	ISSION OF DOCUMEN 15 JAN			1 NAME AND ADDRESS O	OF THE APPL RESPONDEN	LICANT OR THE REPRESENTATIVE NCE IS TO BE ADDRESSED	
PLACE	75 INP	I PARIS		Georges BOURG SAINT-GOBAIN I	EOIS	RCHE	
	ONAL REGISTRATION N	No. 03/00,381		39 QUAI LUCIEN 93300 AUBERVII	LEFRA		
DATE	OF FILING ASSIGNED	BY THE INPI 15 JAN.	2003	_			
	ur file referen ional)	ces: GB2 2003004 FR		•			
Cor	nfirmation of	filing by fax	No. assigned by th	e INPI to the fax			
2	NATURE OF	THE APPLICATION	Tick one of the 4 following boxes				
	Patent applic	ation					
	Utility certifica	ate application					
	Divisional app	plication					
		Initial patent application	No.		Date L		
	or ini	itial utility certificate application	No.		Date		
		of a European patent Initial application	□ No.		Date L	11	
3	TITLE OF TH	IE INVENTION (200 characters	or spaces maximum)				
	BACKPROJECTION AND/OR PROJECTION SCREEN						
4		ECLARATION OR	Country or organisa Date/	•	No.		
		ON FOR THE BENEFIT OF DATE OF A PRIOR	Country or organisa		No.		
	FRENCH AP	PLICATION	Country or organisa	ation	No.		
			☐ If there are other priorities, tick the box and use the "continuation" form				
5	APPLICANT (Tick one of the 2 boxes)			ity		Natural person	
	Name or company name		SAINT-GOBAIN GLASS FRANCE				
	Forenames						
	Legal form						
<u> </u>	SIREN No.						
L	APE-NAF Code		40.47(5) 15.514	CACE			
	Domicile or	Street	18 AVENUE D'AI	_SACE			
	registered	Postcode and town	92400 CO	JRBEVOIE			
<u> </u>	office	Country	FRANCE				
	Nationality		FRENCH				
	Telephone N	 		Fax No. (optional)		
<u> </u>	E-mail addre	ess (optional)				Alan Harriston Alan Harriston	
i			If there are other applicants, tick the box and use the "continuation" form				



Reserved for the INPI

PATENT

UTILITY CERTIFICATE

REQUEST FOR GRANT



page 2/2

SUBMISSION OF DOCUMENTS DATE 15 JAN. 2	2003	<u> </u>				
PLACE 75 INPI P	ARIS					
NATIONAL REGISTRATION No. ASSIGNED BY THE INPI	03/00,	381		DB 540 W / 210502		
6 REPRESENTAT	IVE					
Name		BOURGEOIS				
Forename		GEORGES				
Firm or Company	У	SAINT-GOBAIN RECHERCHE				
·	t power of attorney	422-5/S.006				
and/or contractua	al arrangement					
Address	Street	39 QUAI LUCIEN LEFRANC				
	Postcode and town	9 3 3 0 0 AUBERVILLIERS				
	Country	FRANCE				
Telephone No. (option	nal)	01 48 39 59 52				
Fax No. (optional)		01 48 34 66 96				
E-mail address (option	onal)					
7 INVENTOR (S)		The inventors must be natural persons				
The inventors are the	e applicants	☐ Yes ☑ No ☐ In this case, fill in the Designation of inventor(s) form				
8 SEARCH REPO	RT	For a patent application only (including division and conversion)				
	mmediate compilation					
UI OI	r deferred compilation	Only for natural perso	Only for natural persons filing their own application			
Fee paid in	instalments	☐ Yes				
(in two in	stalments)	□ No				
9 REDUCTION OF	F FEES	For natural persons o	nly			
		☐ Requested for the first time for this invention (attach notice on non-application)				
		☐ Obtained prior to filing for this invention (attach copy of the decision granting free				
10 NUCLEOTIDE A	NID/OP	assistance or indicate its reference): AG				
AMINO ACID SI		☐ Tick the box if the description contains a sequence listing				
The computer readable form is enclosed						
	the information recorded ble form is identical to the sting is enclosed					
give the number	continuation" form, of attached pages					
OR REPRESEN		1		SIGNED FOR THE PREFECTURE OR THE INPI		
Georges BO				C. TRAN		
į						

- 1 -

BACKPROJECTION and/or PROJECTION SCREEN

The present invention relates to a backprojection and/or projection screen. It relates more particularly to a screen suitable for allowing an image to be displayed without any defect on both faces of the screen, this image possibly coming, for example, from a video projector or more generally from a light source positioned so as to face one of the faces of the screen.

For the sake of understanding, the projection screen according to the invention has two faces, namely the main face of the screen on which the image coming from the light source is projected, which main face is generally positioned in the same region in space as the light source, and the opposite face of the screen on which the image projected on the main face appears when viewed in transmission. A backprojection screen has a main face and an opposite face possessing the same characteristics as the abovementioned projection screen but is distinguished therefrom by the fact that the user and the light source are not located in the same region in space but are on either side of the screen.

25

5

10

15

20

For the purposes of the present invention, the term "screen" will be used to encompass both a projection screen and a backprojection screen.

Several types of backprojection screen families for 30 displaying such an image are known. Thus, plastic these rigid are known, diffusers screens or translucent having a plastic screens constituting the framework of the screen into which a plurality of metal oxide (for example SiO₂) particles 35 are incorporated. These screens allow an image to be correctly viewed without any optical defect at a - 2 -

lower optical quality (presence of blurring). In addition, plastic backprojection screens are sensitive to ultraviolet and infrared radiation and to moisture, thereby limiting their lifetime and the perpetuity of their optical quality.

Also known are screens that can be unwound from a reel fastened to a support. They are also made of plastic, but are not translucent. They operate only in reflection and not in transmission.

Another screen technology was developed from diffusers that operate using the technology of liquid crystals. The main advantage of this type of screen lies, on the one hand, in their small thickness (of around 20 $\mu m)$ and, on the other hand, most particularly, in the fact that, under the action of an electric field, they become transparent and no longer diffusing, their use in backprojection being however only a secondary use.

20

25

30

35

15

5

10

However, as drawbacks, the viewing angle is very limited (the viewing angle is around thirty degrees or so) and the image that appears on the opposite face is of poor optical quality, despite the small thickness of the screen (presence of blurring).

870 224 discloses a structure Document US projection screen provided, on the one hand, on its devices with a plurality of optical main face, (cylindrical microlenses and Fresnel lenses) and, the other hand, on its opposite face, a plurality of orifices (transparent and slightly diffusing regions) judiciously positioned relative are respective optical foci of the said cylindrical lenses, allowing the projected image to be displayed.

- 3 -

This screen structure is particularly expensive, the viewing angle is also small (about 35°) and this device is not conducive to direct projection (view in reflection).

5

Finally, a last backprojection screen family consists of holographic diffusers.

The main advantage of this technology lies in the transparency of the screen and the adjustment of the viewing angle. However, here again, this screen structure is expensive, thereby confining it to small-format screens. The presence of blurring on the opposite face of the screen is also noted, despite the transparency of the screen.

The aim of the present invention is therefore to alleviate the drawbacks of the devices known from the prior art by providing a backprojection and/or projection screen suitable for displaying an image on both faces of the screen at a viewing angle possibly up to 180° on both faces, this display being effected without any optical defects on both faces, that is to say with excellent uniformity of the displayed image.

25

30

20

For this purpose, the backprojection and/or projection screen according to the invention is characterized in that it comprises at least a first substrate joined to a scattering layer producing a subsurface effect, said layer being suitable for obtaining a viewing angle of less than or equal to 180° on both faces of the said layer.

To gain a better understanding of the invention, the word "subsurface" will be defined below. A layer is said to be subsurface when its thickness varies within the 0.5 to 50 µm range, especially the range between

- 4 -

- 0.5 and 10 μm and preferably between 0.5 and 5 μm . This definition is to be compared with a scattering layer producing a volume effect.
- 5 In the preferred embodiments of the invention, one or more of the following provisions may optionally also apply:
 - the resolution of the screen is at least $10^5 \, \mathrm{dpi}$;
- the scattering layer is deposited on one of the faces of the first substrate and a lamination interlayer is deposited on the opposite face of the said first substrate, the said interlayer in turn being joined to a second substrate;

15

- the second substrate is a tinted substrate;
- the scattering layer is deposited on one of the faces of a first substrate, the said first substrate being in turn joined to a second substrate so as to form a double-glazing unit;
- the first substrate and the scattering layer are joined to a third substrate, a peripheral bead separating that face of the first substrate which is coated with the said scattering layer from the third substrate;
- the scattering layer consists of elements comprising particles and a binder, the binder allowing the particles to be mutually agglomerated;
 - the particles are metal or metal oxide particles;
- the particles are chosen from silica, alumina, zirconia, titanium and cerium oxides, or a mixture of at least two of these oxides;
 - the particle size is between 50 nm and 1 $\mu m;$
- the thickness of the scattering layer is between 0.5 and 5 $\mu m\,;$
 - at least one of the first, second and third substrates is a glass substrate;

- 5 -

- at least one of the first, second and third substrates is a transparent substrate based on a polymer, for example polycarbonate; and
- at least one of the first, second and third substrates includes a coating having another functionality, especially a coating with a low-emissivity function or an antistatic, antimisting, antifouling or antireflection function.
- 10 Other advantages and features of the invention will become apparent in the light of the detailed description that follows.

Thus, according to one embodiment of the invention, the scattering layer producing a subsurface effect consists 15 of particles agglomerated in a binder, the said particles having a mean diameter of between 0.3 and 2 microns, the said binder being in a proportion of between 10 and 40% by volume and the particles forming aggregates whose size is between 0.5 and 5 microns, the 20 said layer having a contrast attenuation of greater and preferably greater than 50%. This 40% described in Application WO layer is scattering 01/90787 and the contents of that application are incorporated in the present application for reference. 25

The particles are chosen from semitransparent particles and preferably from mineral particles such as oxide, nitride and carbide particles.

30

The particles will preferably be chosen from silica, alumina, zirconia, titanium and cerium oxides, or from a mixture of at least two of these oxides.

35 Such particles may be obtained by any means known to those skilled in the art and especially by precipitation or by pyrolysis. The particle size is

- 6 -

such that at least 50% of the particles depart from the mean diameter by less than 50%.

When the layer is in an external position, the binder is also chosen to have an abrasion resistance sufficient for the backprojection system to be handled without any damage, for example in particular with the other substrates forming the screen are being mounted.

Depending on the requirements, the binder may be chosen to be a mineral binder, for example in order to increase the temperature resistance of the layer, or an organic binder, especially so as to make it simpler to produce the said layer, it being possible for crosslinking to take place simply, for example room-temperature crosslinking.

The binder has a different index from that of the particles and the difference between these two indices is preferably at least 0.1. The index of the particles is greater than 1.7 and that of the binder is preferably less than 1.6.

20

25

The binder is chosen from potassium silicates, sodium silicates, lithium silicates, aluminium phosphates, polymers of the polyvinyl alcohol type, thermosetting resins, acrylics, etc.

To promote the formation of aggregates of the desired size, at least one additive resulting in a random distribution of the particles within the binder may be added. The dispersion additive or dispersant is chosen from the following agents: an acid, a base or ionic polymers of low molecular mass, especially less than 50 000 g/mol.

- 7 -

It is also possible to add other agents and, for example, a wetting agent such as nonionic, anionic or cationic surfactants in order to provide a layer that is homogeneous on a large scale.

5

It is also possible to add rheology modifiers, such as cellulose ethers.

The layer thus defined may be deposited with a thickness of between 1 and 20 microns. The methods of depositing such a layer may be any of those known to those skilled in the art, such as deposition by screen printing, by paint coating, by dip coating, by spin coating, by flow coating, by spraying etc.

15

30

35

When the desired thickness of the deposited layer is greater than 2 microns, a deposition process of the screen-printing type is used.

20 As a variant - a preferred embodiment - of a binder used in a screen-printing deposition process, a binder essentially consisting of a glass frit or flux is used. This glass frit or flux may, for example, be based on a mixture of zinc oxide, boron oxide, silica and sodium oxide.

This binder is applied in the present invention as binder for the scattering layer used in the backprojection and/or projection screen, but it may also be used as binder in a scattering layer integrated into a screen, for example a diffusion screen.

When the thickness of the layer is less than 4 microns, it is preferably deposited by flow coating or by spraying.

It is also possible to produce a layer whose thickness varies depending on the area of coverage on the surface; such an embodiment makes it possible to correct intrinsic inhomogeneties of a light source restored on the screen. For example, it is possible in this way to correct the intensity of light sources according to the viewer's viewing angle and thus to adjust the gain. The gain is defined in the following manner:

10

- gain luminance obtained with the screen viewed centrally/luminance obtained with a Lambertian screen with a gain of 1, viewed centrally.
- 15 Thus, the gain may also be defined in the following
 manner:
 gain = central luminance x area of the screen / flux of
 the projector.
- 20 From these definitions, the projection screen is said to have a gain of 1 when it allows a 180° viewing angle (Lambertian screen).
- In addition, if the screen allows the light rays to be reoriented in a more restricted viewing angle, thus increasing the luminance of the image within these angles, the screen will then have a gain of greater than 1.
- According to another embodiment, selective deposition of the subsurface layer may be envisaged, and in this case it will be deposited only over part of the substrate, the transparent remaining part.
- 35 According to the invention, the scattering layer is deposited on a first transparent substrate, which may

According to the invention, the scattering layer is deposited on a first transparent substrate, which may or may not have a flat shape depending on the application.

5

The scattering layer producing a subsurface effect makes it possible to produce a screen whose resolution is at least 10^5 dpi (dots per inch) or 10^6 dpi.

To improve mechanical integrity of the first substrate coated with the scattering layer producing a subsurface effect, as described above, a lamination interlayer is joined to the first substrate on its opposed face (that face not covered with the scattering layer), it being possible for this interlayer to be made of PVB (polyvinyl butyral) or PU (polyurethane), for example, and in turn to be joined to a second, preferably tinted, substrate. As a non-limiting example, this may, for example, be a glass allowing the contrast to be improved, such as a grey glass with a TL of 10%.

A third substrate is joined to this laminated element consisting of the first substrate, the lamination interlayer and the second substrate.

25

30

35

A sealing bead, made of plastic (for example PU or EPDM) is deposited by known means (for example extrusion) around the periphery of that face of the first substrate which includes its scattering layer. A third substrate is deposited on this sealing bead. This bead of material provides the assembly with mechanical integrity and maintains a cavity filled with a gaseous fluid (especially air) between the two substrates, thereby enhancing the scattering phenomena within the scattering functional layer.

- 10 -

substrates or polymer (PMMA or polycarbonate) substrates.

Whatever the embodiment, the backprojection and/or projection screen according to the invention allows an image to be restored with a uniformity of at least 80% and preferably around 85%.

An image is said to be uniform when observation made by
eye of this image on a screen having the dimensions of
600x450 mm shows no variation in intensity of the image
owing to the quality of the layer, for example. The eye
starts to "see" intensity variations only when the
intensity difference from one point on the screen to
another is greater than 15%.

The display screen is suitable for viewing an image projected on both faces of the screen, with a viewing angle of less than or equal to 180°C.

20

25

30

35

In the present invention, the viewing angle is the angle for which the luminance is equal to one half of the luminance at the centre. In this case, the display is formed without any optical defect (blurring, distortion, edge effect, chromatic aberration, local luminance inhomegeneity on either of the faces.

An alternative embodiment consists in incorporating, into the assembly at one of the faces of one of the first, second or third substrates, a coating having a functionality. This may be a coating with the function of blocking radiation of wavelengths in the infrared (for example using one or more silver layers surrounded by dielectric layers, or layers made of nitrides, such as TiN or ZrN, or layers made of metal oxides or steel or an Ni-Cr alloy), or having a low-emissivity function (for example a doped metal oxide such as F:SnO₂ or tin-

1st filing

- 11 -

doped indium oxide ITO or one or more silver layers), an antifogging function (by means of a hydrophilic layer), an antifouling function (photocatalytic coating, comprising TiO_2 at least partially crystallized in anatase form) or else an antireflection multilayer, for example of the $\text{Si}_3N_4/\text{SiO}_2/\text{Si}_3N_4/\text{SiO}_2$ type.

The envisaged applications of the invention are in particular the backprojection or projection systems used, for example, for displaying an image coming, for example, from video projectors, for the use of image walls in stadiums, for information display panels joined together as a wall or suspended for municipal domestic use. Of course, the projection and/or backprojection screen may be used as a partition or a wall separating two enclosures.

10

15

The screen according to the invention described above offers many advantages:

- because the various constituent elements are made using an essentially mineral technology, the sensitivity of this screen to moisture and to UV radiation is very low; and
- the use of a scattering layer producing a subsurface effect, the viewing angle of which may be up to 180°, limits "hot spot" phenomena (By "hot spot" is meant that the viewer can perceive, along the projection axis and through the screen, the light source).

CLAIMS

- 1. Backprojection and/or projection screen characterized in that it comprises at least a first substrate joined to a scattering layer producing a subsurface effect, said layer being suitable for obtaining a viewing angle of less than or equal to 180° on both faces of the said layer.
- 10 2. Screen according to Claim 1, characterized in that the resolution of the screen is at least 10^5 dpi.
- 3. Screen according to either of Claims 1 and 2, characterized in that the scattering layer is deposited on one of the faces of the first substrate and a lamination interlayer is deposited on the opposite face of the said first substrate, the said interlayer in turn being joined to a second substrate.
- 20 4. Screen according to Claim 3, characterized in that the second substrate is a tinted substrate.
- 5. Screen according to one of the preceding claims, characterized in that the first substrate and the scattering layer are joined to a third substrate, a peripheral bead separating that face of the first substrate which is coated with the said scattering layer from the third substrate.
- 30 6. Screen according to one of the preceding claims, characterized in that the scattering layer consists of elements comprising particles and a binder, the binder allowing the particles to be mutually agglomerated.
- 35 7. Screen according to Claim 6, characterized in that the particles are metal or metal oxide particles.

1st filing

- 13 -

8. Screen according to either of Claims 6 and 7, characterized in that the particles are chosen from silica, alumina, zirconia, titanium and cerium oxides, or a mixture of at least two of these oxides.

5

- 9. Screen according to one of Claims 6 to 8, characterized in that the particle size is between 50 nm and 1 $\mu m\,.$
- 10 10. Screen according to Claim 6, characterized in that the binder essentially consists of a glass frit or flux.
- 11. Screen according to Claim 10, characterized in that the glass frit or flux is based on a mixture of zinc oxide, boron oxide, sodium oxide and silica.
- 12. Screen according to one of the preceding claims, characterized in that the thickness of the scattering layer is between 0.5 and 5 μm .
 - 13. Screen according to one of the preceding claims, characterized in that at least one of the first, second and third substrates is a glass substrate.

25

14. Screen according to one of claims 1 to 12, characterized in that at least one of the first, second and third substrates is a transparent substrate based on a polymer.

30

35

15. Screen according to one of the preceding claims characterized in that at least one of the first, second and third substrates includes a coating having another functionality, especially a coating with a low-emissivity function or an antistatic, antimisting, antifouling or antireflection function.



PATENT



UTILITY CERTIFICATE

Intellectual Property Code - Book VI

PATENTS DEPARTMENT

BOURGEOIS Georges Power of attorney 422-5/S.006

26 bis, rue de Saint Pétersbourg 75800 Paris Cedex 08 Telephone: 01 53 04 53 04 Fax: 01 42 93 59 30

DESIGNATION OF THE INVENTOR(S) Page No. . 1 . / . 1

(if the applicant is not the inventor or the sole inventor)

This form is to be filled in legibly in black ink

DB 113 W / 260899 GB2 2003004 FR Your file references (optional) NATIONAL REGISTRATION NO. 03/00.381 TITLE OF THE INVENTION (200 characters or spaces maximum) BACKPROJECTION AND/OR PROJECTION SCREEN THE APPLICANT(S): SAINT-GOBAIN GLASS FRANCE 18 AVENUE D'ALSACE 92400 COURBEVOIE DESIGNATE(S) AS INVENTOR(S): (Indicate top right "Page 1/1". If there are more than 3 inventors, use an identical form and number each page, indicating the total number of pages.) **BERTIN-MOUROT** Name Forenames **THOMAS** 20 RUE DE LA GLACIERE Street Address **PARIS** 75013 Postcode and town Employer company (optional) **LEBAIL** Name Forenames YANNIK 73 RUE DU JEU DE L'ARC Street Address Postcode and town 60150 CHEVINCOURT Employer company (optional) Name Forenames Street Address Postcode and town Employer company (optional) DATE AND SIGNATURE(S) OF THE APPLICANT(S) OR OF THE REPRESENTATIVE (Name and capacity of the signatory) 14 January 2003 [signature]